

Description

Permabond CA Solvent 100 is extremely effective for dissolving cyanoacrylate bonds or removing cured excess adhesive. It is not recommended for use on acrylic plastics.

Physical Properties

Chemical base	Nitromethane
Appearance	Clear to light yellow liquid
Boiling point	114°C (237°F)
Flashpoint	100°C (212°F)
Ignition temperature	418°C (784.4°F)
Vapor density	2.1 (Air = 1)
Specific Gravity	1.14

Storage & Handling

Storage Temperature Store in a cool place away from direct sunlight	5 to 25°C (41 to 77°F)
--	------------------------

Directions for Use

- Applying CA Solvent 100 remover to cured cyanoacrylate adhesive will allow its removal in several minutes to several hours, depending upon the amount of adhesive.
- Thin layers of adhesive will wipe off with the remover soaked tissue or cloth.
- Thick beads or drops will take between 15 and 30 minutes and will require reapplication of solvent.
- Bonded parts may require several hours of soaking.
- This solvent can affect certain plastics, coatings and fabrics. It is recommended that all surfaces be tested for compatibility before use.

Additional Information

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Safety Data Sheet.

www.permabond.com

• UK: 0800 975 9800

• General Enquiries: +44 (0)1962 711661

• US: 732-868-1372

• Asia: + 86 21 5773 4913

info.europe@permabond.com

info.americas@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.